

BRADY B-112 NON-SILICONE SELF-WOUND POLYESTER OVERLAMINATE

TDS No. B-112
Effective Date: 01/11/2019

Description:

GENERAL

Print Technology: n/a

Material Type: Clear Polyester

Finish: Glossy Clear

Adhesive: Acrylic

APPLICATIONS

Brady B-112 is used as a protective overlaminate. B-112 in a 2-ply put up can be used for paint masking or other similar applications in which the topside overlaminate is removed and the bottomside overlaminate remains and which prohibit the use of any silicones.

REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.brady.co.jp/products/labelsuse/rohs

All other regions: www.bradyid.com/weee-rohs

SPECIAL FEATURES

B-112 is supplied in self-wound format to be used with Brady Protector™ laminator which prints, overlaminates, and diecuts labels. B-112 has a topside non-silicone release which provides unwinding of self-wound rolls.

Brady B-112 is recommended for use with most standard Brady label materials. B-112 has excellent clarity, as well as very good temperature resistance, chemical resistance and abrasion resistance.

B-112 is supplied in self-wound format to be used with Brady Protector™ laminator which prints, overlaminates, and diecuts labels. B-112 has a topside non-silicone release which provides unwinding of self-wound rolls.

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Film -Adhesive -Total	0.0010 inch (0.025 mm) 0.0007 inch (0.018 mm) 0.0017 inch (0.043 mm)
Adhesion to: -Stainless Steel	ASTM D 1000 20 minute dwell	25 oz/in (27 N/100 mm)
Tack	ASTM D 2979 Polyken™ Probe Tack 1 second dwell	17.6 oz (500 g)
Release force of B-112 adhesive from B-112 topside non-silicone release	PSTC-1	7 oz/in (200 grams/25.4 mm)
Tensile Strength and Elongation	ASTM D 1000 -Machine Direction	24 lbs/in (420 N/100 mm), 115%
Abrasion Test	Taber Abraser, CS-17 grinding wheels, 1000 g/arm (Fed. Std. 191A, Method 5306)	Material worn through in one or more spots at approximately 700 cycles
Application Temperature	Lower application temperature	40°F (5°C)

B-112 samples for Performance Properties were tested applied directly to aluminum panels and overlaminated over Brady B-423 white polyester. Samples allowed to dwell 24 hours at room temperature prior to testing.

PERFORMANCE PROPERTIES	TEST METHODS	TYPICAL RESULTS
Long Term High Service Temperature	30 days at various temperatures	Very slight discoloration at 100°C. Slight discoloration and blistering at 130°C but still functional.
Long Term Low Service Temperature	30 days at -94°F (-70°C)	No visible effect at -70°C
Humidity Resistance	30 days at 100°F (37°C), 95% R.H.	No visible effect
UV Light Resistance	30 days in UV Sunlighter™ 100	No visible effect
Weatherability	ASTM G155, Cycle 1 30 days in Xenon Arc Weatherability	Very Slight discoloration
Salt Fog Resistance	ASTM B 117 30 days in 5% salt fog solution chamber	No visible effect
Paint Mask Simulation	1 hour at 266°F (130°C) Heated in 2 ply put-up and then topside overlaminate removed	No visible effect at 266°F (130°C). Topside overlaminate may leave adhesive residue at higher temperatures.

PERFORMANCE PROPERTY	CHEMICAL RESISTANCE
----------------------	---------------------

Samples were tested overlaminated over Brady B-423 white polyester. Samples allowed to dwell 24 hours at room temperature prior to testing. Testing consisted of 5 cycles of 10 minute immersions in the specified chemicals followed by 30 minute recovery periods. Except where noted otherwise, testing was conducted at room temperature.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE
Methyl Ethyl Ketone	Severe adhesive ooze, slight edge lift
1,1,1-Trichloroethane	Slight adhesive ooze
Isopropyl Alcohol	No visible effect
Gasoline	Slight adhesive ooze
SAE 20 WT Oil @70°C	No visible effect
Brake Fluid	No visible effect
Ethylene Glycol	No visible effect
Northwoods™ Buzz Saw Citrus Degreaser	No visible effect
Speedi Kut Cutting Oil 332	No visible effect
Skydrol® 500B-4	Slight adhesive ooze
JP-8 Jet Fuel	No visible effect
5% Alconox® Detergent	No visible effect

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

Alconox® is a registered trademark of Alconox Co.
 Brady Protector™ is a trademark of Brady Worldwide, Inc.
 Northwoods™ is a trademark of the Superior Chemical Corporation.
 Polyken™ is a trademark of Testing Machines Inc.
 Skydrol® is a registered trademark of the Monsanto Company
 Sunlighter™ is a trademark of the Test Lab Apparatus Company
 ASTM: American Society for Testing and Materials (U.S.A.)
 PSTC: Pressure Sensitive Tape Council (U.S.A.)
 SAE: Society of Automotive Engineers (U.S.A.)

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party,

independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2019 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289