

**SETON B-181 DURAGUARD® PROPERTY IDENTIFICATION TAGS**

TDS No. B-181  
Effective Date: 07/23/2001

**Description:**

Seton B-181 DuraGuard® property identification tags consist of a metalized film surface printed legend with protective tamper resistant laminate for indoor and outdoor use.

**Details:**

**Use:**

Seton B-181 is used for identification on computers, office equipment, desks, chairs, tables, file cabinets, tools, fire extinguishers, machinery, and electrical appliances.

**Substrate Type:**

Metalized film with a plastic overlamine

**Standard Material:**

Red, green, black, light blue, dark blue, and burgundy

**Standard Legend Colors:**

Silver & Black

**Thickness (PSTC-33):**

Total: 0.0098 in. (0.25mm)

**Tensile Strength (PSTC-31):**

Break - 120 lbs/in. (2100 N/100mm)

**Elongation (PSTC-31):**

Break - 100%

**Adhesive Properties:**

Adhesion to Steel (PSTC-1)  
15 Minute Dwell (Avg.) -- 100 oz/in. (109 N/100mm)  
Ultimate Dwell (72 Hrs.)(Avg.) -- 121 oz/in. (132 N/100mm)  
Tack (ASTM D2979)(Avg.) -- 1700 gm (16.7 N)  
Drop Shear (PSTC-7)(Avg.) --- 1,000 hrs.

**Abrasion Resistance (Method 5306 of U.S. Federal Test Method Std. No. 191A):**

CS-17 wheels, 500 g wts.  
Legend withstands up to 1900 cycles.

**Chemical Resistance:**

REAGENT	7 DAY IMMERSION	DIP TEST	RUB TEST
30% Sulfuric Acid	NE	NE	NE
10% Sulfuric Acid	NE	NE	NE
30% HCl	F	NE	NE
10% HCl	NE	NE	NE
50% NaOH	F	NE	NE
10% NaOH	F	NE	NE
Methyl Ethyl Ketone	F	F	F
Acetone	F	F	F
1,1,1-Trichloroethane	F	F	NE
Methanol	F	NE	NE
IPA (Isopropanol)	F	F	NE
ASTM #3 Oil	NE	NE	NE
SAE 20 Oil	NE	NE	NE

Alconox®	NE	NE	NE
Toluene	F	F	F
Mineral Spirits	NE	NE	NE
Glacial Acetic Acid	F	F	NE
5% Acetic Acid	NE	NE	NE
Diesel Fuel	NE	NE	NE
Heptane	F	NE	NE
Cellosolve Acetate	F	F	NE
Conc. Ammonia	NE	NE	NE
10% Ammonia	NE	NE	NE
Turpentine	F	NE	NE
Kerosene	NE	NE	NE
Water	NE	NE	NE
Gasoline	F	NE	NE

NE = No Effect

NT = Not Tested

F = Failed (affected Sample)

7 Day Immersion: Immersed in reagent for 7 days.

Dip Test: Five 10 minute dips in reagent with 30 minute recovery.

Rub Test: Rubbed sample for 1 minute with swab soaked in reagent.

**Expected Gloss:**

130 Gardner Units minimum (60° gloss)

**Minimum Application Temperature:**

50°F (10°C)

**Service Temperature:**

-40°F to 293°F (-40°C to 145°C)

**Average Outdoor Durability:**

3-5 years (Average expected outdoor life of product will depend on user definition of failure, climatic conditions, mounting techniques and material color.)

**Shelf Life:**

One year when stored at 70°F (21°C) and 40% to 50% R.H.

**Trademarks:**

Alconox® is a registered trademark of Alconox Co.

DuraGuard® is a registered trademark of Tricor Direct Inc.

ASTM: American Society for Testing and Materials (U.S.A.)

Fed. Spec.: United States Federal Specification (U.S.A.)

PSTC: Pressure Sensitive Tape Council (U.S.A.)

SAE: Society of Automotive Engineers (U.S.A.)

All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units.

**Note:** All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

**WARRANTY**

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their

adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2016 Tricor Direct, Inc. | All Rights Reserved  
Material may not be reproduced or distributed in any form without written permission.

---

Seton Identification Products | 20 Thompson Rd. | Branford, CT 06405-0819 | USA | Tel: 1-800-571-2596 | Fax: 1-800-345-7819