

**SETON B-23 QUICKGUARD(TM) ASSET IDENTIFICATION TAGS**

TDS No. B-23  
 Effective Date: 11/05/2001

**Description:**

Seton Quickguard™ Asset Identification Tags are anodized aluminum material with a printed legend that withstands both indoor and outdoor exposure.

**Details:**

**Use:**

Seton B-23 is used as an asset identification tag, where consecutive numbering may be needed, for use on computers, office furniture and equipment.

**Substrate Type:**

Anodized aluminum

**Adhesive Type:**

- 3M #467- permanent pressure -sensitive adhesive for most smooth non-plastic surfaces.
- 3M #468- permanent pressure -sensitive adhesive for rough or textured non-plastic surfaces.
- 3M #9471- permanent pressure -sensitive adhesive for smooth plastic surfaces.
- 3M #9472LE- permanent pressure -sensitive adhesive for smooth plastic surfaces.

**Standard Material Colors:**

Black, Light Blue, Dark Blue, Dark Green, Dark Red, Flame Red

**Total Thickness (PSTC-33):**

- 3M #467- .005" (0.127 mm)
- 3M #468- .008" ( 0.203 mm)
- 3M #9471- .005" (0.127 mm)
- 3M #9472LE- .008" ( 0.203 mm)

**Adhesive Properties:**

Adhesion to Stainless Steel - PSTC-1 (Avg.)

	<b>3M #467</b>	<b>3M #468</b>	<b>3M #9471</b>	<b>3M #9472LE</b>
15 minute dwell	destroyed	destroyed	destroyed	destroyed
Ultimate Dwell (72 hours)	destroyed	destroyed	destroyed	destroyed

Tack - ASTM D 2979 (Avg.)

	<b>3M #467</b>	<b>3M #468</b>	<b>3M #9471</b>	<b>3M #9472LE</b>
15 minute dwell	1618 g (15.9N)	1538 g (15.1N)	1234 g (12.1N)	1750 g (17.2N)

**Chemical Resistance**

<b>REAGENT</b>	<b>7 DAY IMMERSION</b>	<b>DIP TEST</b>	<b>RUB TEST</b>
30% Sulfuric Acid	F	F	NE
10% Sulfuric Acid	F	F	NE
30% Hydrochloric Acid	F	F	NE
10% Hydrochloric Acid	F	F	NE
50% Sodium Hydroxide	F	F	NE
10% Sodium Hydroxide	F	F	NE
Methyl Ethyl Ketone	F	NE	NE
Acetone	F	NE	NE
Toluene	F	F	NE
1,1,1-Trichloroethane	F	NE	NE
Methanol	F	NE	NE
Isopropyl Alcohol	NE	NE	NE

Heptane	F	NE	NE
Mineral Spirits	F	NE	NE
Kerosene	F	NE	NE
Diesel Fuel	F	NE	NE
ASTM #3 Oil	NE	NE	NE
SAE 20 Oil	NE	NE	NE
10% Sodium Chloride	F	NE	NE
Alconox®	NE	NE	NE
Bleach	NE	NE	NE
Water	NE	NE	NE

NE = No Effect

F = Failed (affected Sample)

7 Day Immersion: Immersed in reagent for 7 days.

Dip Test: Five 10 minute dips in reagent with 30 minute recovery.

Rub Test: Rubbed sample for 1 minute with swab soaked in reagent.

**Abrasion Resistance (Method 5306 of U.S. Federal Test Method Std. No. 191A):**

CS-10 wheels, 500 g wts.

Legend withstands up to 350 cycles.

**60°Gloss:**

38 Gardner Units

**Minimum Application Temperature:**

40°F (4°C)

**Service Temperature:**

-40°F to 300°F (-40°C to 149°C)

**Application Temperature**

40°F (4°C)

**Average Outdoor Durability:**

3-5 years (Average expected outdoor life of product will depend on user definition of failure, climatic conditions, mounting techniques and material color.)

**Shelf Life:**

2 years when stored at 70°F (21°C) and 40% to 50% R.H.

**Trademarks:**

Alconox® is a registered trademark of Alconox Co.

Quickguard™ is a trademark of TRICOR Direct, Inc.

ASTM: American Society for Testing and Materials (U.S.A.)

Fed. Spec.: United States Federal Specification (U.S.A.)

PSTC: Pressure Sensitive Tape Council (U.S.A.)

SAE: Society of Automotive Engineers (U.S.A.)

All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units.

Note: All values shown are averages and should not be used for specification purposes.

**Note:** All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

**WARRANTY**

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2016 Tricor Direct, Inc. | All Rights Reserved  
Material may not be reproduced or distributed in any form without written permission.

---

Seton Identification Products | 20 Thompson Rd. | Branford, CT 06405-0819 | USA | Tel: 1-800-571-2596 | Fax: 1-800-345-7819