

BRADY B-330 BRADYWRAP MARKER

TDS No. B-330
Effective Date: 03/25/2019

Description:

GENERAL

Print Technology: Thermal transfer and dot matrix

Material Type: Heat shrinkable polyolefin

Adhesive: Heat activated polyester

APPLICATIONS

Identification of wire bundles, large conduits and installed cables

RECOMMENDED RIBBONS

Brady Series R5000 for dot matrix printing

Brady Series R4300 and the Brady Series R6200 for thermal transfer printing

REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.bradyc.co.jp/products/labelsuse/rohs

All other regions: www.bradycid.com/weee-rohs

SPECIAL FEATURES

B-330 incorporates a matrix of pressure sensitive adhesive dots which promotes initial tack and adhesion during application.

B-330 Bradywrap™ Marker can be heat activated using a heat tool or an oven (2 minutes at 275°F) to create the most permanent adhesive bond. B-330 can also be used without heat activation. A 72 hour dwell is recommended when product is not heat activated.

B-330 is available in white and yellow.

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Substrate -Adhesive -Total	0.0065 in (0.165 mm) 0.0015 in (0.038 mm) 0.0080 in (0.203 mm)
Adhesion to: Aluminum QQ-A-250/5 panels	ASTM D 1000 Heated for 2 minutes at 275°F (135°C) 72 hour room temperature dwell	139 oz/inch (152 N/100 mm) 89 oz/inch (97 N/100 mm)
Tensile Strength and Elongation	ASTM D 1000 -Machine direction	24 lb/inch (420 N/100 mm), 540%
Dielectric Strength	ASTM D 1000	12,000 volts

Performance properties were tested on B-330 printed with the Brady Series R4300, the Brady Series R6200 ribbons and with the Brady Series R5000 ribbon. Printed samples of B-330 were wrapped around two 0.5 inch OD black MTW wires. One sample dwelled at room temperature for 72 hours and the other was heated at 135°C for 2 minutes before exposure to the indicated environmental conditions. Unless noted, results are the same for room temperature and heated samples.

PERFORMANCE PROPERTIES	TEST METHODS	TYPICAL RESULTS
Short Term High Temperature	24 hours at 248°F (120°C)	No visible effect, material distorts at higher temperatures
Long Term High Service Temperature	1000 hours at 230°F (110°C)	Slight topcoat discoloration, no visible effect to print
Low Service Temperature	30 days at -94°F (-70°C)	No visible effect

Humidity Resistance	30 days at 100°F, 95% R.H.	No visible effect
UV Light Resistance	30 days in Sunlighter™ 100	No visible effect
Weatherability ¹	ASTM G155, Cycle 1 30 days in Xenon Arc Weatherometer	No visible effect (white), slight topcoat fade (yellow)
Salt Fog Resistance	ASTM B117 30 days in 5% salt fog solution chamber	No visible effect
Print Adherence per SAE-AS81531 (Sec 3.4.2) R4300 and R6200 Series thermal transfer ribbons	SAE-AS81531 (Sec 4.6.2) 20 eraser rubs with hard hand pressure	Pass- Print still legible
Solvent Resistance per SAE-AS81531 (sec 3.4.3) R4300 and R6200 Series thermal transfer ribbons	MIL-STD-202, Method 215K 3 cycles of 3 minute immersions in specified fluids followed by toothbrush rub after each immersion	Pass- Print still legible

¹B-330 is not recommended for outdoor use.

PERFORMANCE PROPERTY	CHEMICAL RESISTANCE
-----------------------------	----------------------------

Samples printed with the Brady Series R4300, the Brady Series R6200 thermal transfer ribbons and the Series R5000 dot matrix ribbons.

Printed samples of B-330 white were wrapped around two 0.5" OD black MTW wires. One sample dwelled at room temperature for 72 hours and the other was heated at 135°C for 2 minutes. Test was conducted at room temperature. Testing consisted of 5 cycles of 10 minute immersions in the specified test fluid followed by a 30 minute recovery period. After final immersion, samples rubbed 10 times with cotton swab saturated with test fluid.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE (Effect to Label Stock)	
	72 HOURS AT ROOM TEMPERATURE	2 MINUTES AT 135°C
	Methyl Ethyl Ketone	Less than 1/32" unwrap
1,1,1-Trichloroethane	Less than 1/32" unwrap	Less than 1/32" unwrap
Isopropyl Alcohol	No unwrap	No unwrap
JP-8 Jet Fuel	No unwrap	No unwrap
Mil 5606 Oil	Less than 1/32" unwrap	No unwrap
Mil 7808 Oil	Less than 1/32" unwrap	Less than 1/32" unwrap
Gasoline	No unwrap	No unwrap
Skydrol® 500B-4	No unwrap	Less than 1/32" unwrap
Super Agitene®	No unwrap	No unwrap
BIOACT® EC-7R™ Terpene Cleaner	No unwrap	No unwrap
Deionized Water	No unwrap	No unwrap
3% Alconox® Detergent	No unwrap	No unwrap
10% Sodium Hydroxide Solution	No unwrap	No unwrap
10% Sulfuric Acid Solution	No unwrap	No unwrap
5% Salt Water Solution	No unwrap	No unwrap
Propylene Glycol	No unwrap	No unwrap

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE (Thermal Transfer Printed)			
	R4300 RIBBON		R6200 RIBBON	
	WITHOUT RUB	WITH RUB	WITHOUT RUB	WITH RUB
Methyl Ethyl Ketone	No visible effect	Print and topcoat removed	No visible effect	Print and topcoat removed
1,1,1-Trichloroethane	No visible effect	Print and topcoat removed	No visible effect	Print and topcoat removed
Isopropyl Alcohol	No visible effect	Slight print removal	No visible effect	No visible effect
JP-8 Jet Fuel	No visible effect	No visible effect	No visible effect	No visible effect
Mil 5606 Oil	No visible effect	No visible effect	No visible effect	No visible effect
Mil 7808 Oil	No visible effect	No visible effect	No visible effect	No visible effect
Gasoline	No visible effect	Severe print removal	No visible effect	Moderate print removal
Skydrol® 500B-4	No visible effect	Severe print removal	No visible effect	Severe print removal
Super Agitene®	No visible effect	Slight print removal	No visible effect	No visible effect
BIOACT® EC-7R™ Terpene Cleaner	No visible effect	Severe print removal	No visible effect	Moderate print removal
Deionized Water	No visible effect	No visible effect	No visible effect	No visible effect
3% Alconox® Detergent	No visible effect	No visible effect	No visible effect	No visible effect

10% Sodium Hydroxide Solution	No visible effect	No visible effect	No visible effect	No visible effect
10% Sulfuric Acid Solution	No visible effect	No visible effect	No visible effect	No visible effect
5% Salt Water Solution	No visible effect	No visible effect	No visible effect	No visible effect
Propylene Glycol	No visible effect	No visible effect	No visible effect	No visible effect

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE (Dot Matrix Printed)	
	R5000 RIBBON	
	WITHOUT RUB	WITH RUB
Methyl Ethyl Ketone	No visible effect	Print and topcoat removed
1,1,1-Trichloroethane	No visible effect	Print and topcoat removed
Isopropyl Alcohol	No visible effect	No visible effect
JP-8 Jet Fuel	No visible effect	No visible effect
Mil 5606 Oil	No visible effect	No visible effect
Mil 7808 Oil	No visible effect	No visible effect
Gasoline	No visible effect	Slight print removal
Skydrol® 500B-4	No visible effect	Severe print removal
Super Agitene®	No visible effect	No visible effect
BIOACT® EC-7R™ Terpene Cleaner	No visible effect	Moderate print removal
Deionized Water	No visible effect	No visible effect
3% Alconox® Detergent	No visible effect	No visible effect
10% Sodium Hydroxide Solution	No visible effect	No visible effect
10% Sulfuric Acid Solution	No visible effect	No visible effect
5% Salt Water Solution	No visible effect	No visible effect
Propylene Glycol	No visible effect	No visible effect

Shelf Life

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

Alconox® is a registered trademark of Alconox Co.
 BIOACT® is a registered trademark of Petroferm, Inc.
 BradyPrinter™ is a trademark of Brady Worldwide, Inc.
 Bradywrap™ is a trademark of Brady Worldwide, Inc.
 EC-7R™ is a trademark of Petroferm Inc.
 Skydrol® is a registered trademark of the Monsanto Company
 Sunlighter™ is a trademark of the Test Lab Apparatus Company
 Super Agitene® is a registered trademark of Graymills Corporation
 ASTM: American Society for Testing and Materials (U.S.A.)
 All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units.

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2019 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289