

BRADY B-409 MATTE POLYOLEFIN LABEL STOCK

TDS No. B-409
Effective Date: 03/07/2019

Description:

GENERAL

Print Technology: Dot Matrix and Laser

Material Type: Polyolefin

Finish: Matte

Adhesive: Permanent Acrylic

APPLICATIONS

Designed for use in labeling applications requiring excellent solvent resistance and print permanency. B-409 is not recommended for outdoor exposure use. Dot-matrix printing of barcodes is not recommended.

RECOMMENDED RIBBONS

Brady Series R5000

REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.brady.co.jp/products/labelsuse/rohs

All other regions: www.bradyid.com/weee-rohs

SPECIAL FEATURES

Brady B-409 provides outstanding performance in laser and xerographic printing processes. B409 also provides permanency and smudge resistance with dot matrix printing method. B-409 meets the requirements of MIL-STD-202F, Method 215J.

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Substrate -Adhesive -Total	0.0083 inch (0.210 mm) 0.0010 inch (0.025 mm) 0.0093 inch (0.235 mm)
Adhesion to: -Stainless Steel	ASTM D 1000 20 minute dwell 24 hour dwell	30 oz/in (33 N/100 mm) 40 oz/in (44 N/100 mm)
-Textured ABS	20 minute dwell 24 hour dwell	5 oz/in (5 N/100 mm) 5 oz/in (5 N/100 mm)
-Polypropylene	20 minute dwell 24 hour dwell	25 oz/in (27 N/100 mm) 30 oz/in (33 N/100 mm)
Tack	ASTM D 2979 Polyken™ Probe Tack 1 second dwell	16 oz (450 g)
Tensile Strength and Elongation	ASTM D 1000 -Machine Direction	25 lbs/in (438 N/100 mm), 80%
Application Temperature	Lowest application temperature to stainless steel	50°F (10°C)

The following testing is performed with B-409 laser printed on the Hewlett Packard laserjet 4 and dot matrix printed with the Brady Series 5000 ribbon. Samples laminated to aluminum panels. All samples allowed to dwell 24 hours prior to testing.

PERFORMANCE PROPERTIES	TEST METHODS	TYPICAL RESULTS
High Service Temperature	30 days at 193°F (90°C)	No visible effect
Low Service Temperature	30 days at -94°F (-70°C)	No visible effect

Humidity Resistance	30 days at 100°F (37°C), 95% R.H.	No visible effect
UV Light Resistance	30 days in UV Sunlighter™ 100	Label material chalky, no visible effect to print.
Weatherability	ASTM G155, Cycle 1 30 days in Xenon Arc Weatherometer	Label destroyed
Abrasion Resistance	Taber Abraser, CS-10 grinding wheels, 250 g/arm (Fed. Std. 191A, Method 5306)	Print still legible at 4000 cycles.
MIL-STD-202, Method 215J	Solvent immersion/toothbrush rub test in: - IPA/mineral spirits solution - Terpene cleaner - Alkaline detergent solution	No visible effect to dot matrix print, laser toner removed in IPA/mineral spirits and terpene cleaner.
PERFORMANCE PROPERTY		CHEMICAL RESISTANCE

The following testing is performed with B-409 laser printed on the Hewlett Packard Laserjet 4 and dot matrix printed with the Brady Series 5000 ribbon. Samples laminated to aluminum panels. All samples allowed to dwell 24 hours prior to testing. Testing consisted of 5 cycles of 10 minute immersions in the specified chemicals followed by 30 minute recovery periods. After the final immersion the samples were rubbed 10 times with cotton swabs saturated with test fluid. Testing was conducted at room temperature.

CHEMICAL REAGENT	SUBJECTIVE OBSERVATION OF VISUAL CHANGE		
	APPEARANCE OF TAPE	APPEARANCE OF LASER PRINT	APPEARANCE OF DOT MATRIX PRINT
Methyl Ethyl Ketone	Slight adhesive ooze	No visible effect w/o rub, print removed when rubbed	No visible effect
1,1,1-Trichloroethane	Slight adhesive ooze	Slight bleed w/o rub, print removed when rubbed	No visible effect
Toluene	Slight adhesive ooze	Slight bleed w/o rub, print removed when rubbed	No visible effect
Isopropyl Alcohol	No visible effect	No visible effect	No visible effect
Mineral Spirits	No visible effect	Slight bleed w/o rub, print removed when rubbed	No visible effect
JP-8 Jet Fuel	Slight adhesive ooze	Slight bleed w/o rub, print removed when rubbed	No visible effect
SAE 20 WT Oil	Slight label discoloration	No visible effect	No visible effect
Mil 5606 Oil	Label discolored red	No visible effect	No visible effect
Speedi Kut Cutting Oil 332	Label discoloration	No visible effect	No visible effect
Gasoline	Slight label discoloration	Slight bleed w/o rub, print removed when rubbed	No visible effect
Rust Veto® 377	Slight label discoloration	Print removed when rubbed	No visible effect
Super Agitene®	No visible effect	No visible effect w/o rub, print removed when rubbed	No visible effect
Deionized Water	No visible effect	No visible effect	No visible effect
3% Alconox® Detergent	No visible effect	No visible effect	No visible effect
10% Sodium Hydroxide Solution	No visible effect	No visible effect	No visible effect
10% Sulfuric Acid Solution	Slight label discoloration	No visible effect	No visible effect

Shelf Life

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

Alconox® is a registered trademark of Alconox Co.
Polyken™ is a trademark of Testing Machines Inc.
Rust Veto® is a registered trademark of the E.F. Houghton & Co.
Sunlighter™ is a trademark of the Test Lab Apparatus Company
Super Agitene® is a registered trademark of Graymills Corporation
ASTM: American Society for Testing and Materials (U.S.A.)
SAE: Society of Automotive Engineers (U.S.A.)
All S.I. units are mathematically derived from the U.S. conventional units.

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2019 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289