

BRADY B-7661 GLOSS PAPER FOR INKJET PRINTING

TDS No. B-7661

Effective Date: 21/02/2022

Description:

GENERAL

Print Technology: Inkjet printing

Material Type: White Paper

Finish: Gloss

Adhesive: Permanent Acrylic

APPLICATIONS

BRADY B-7661 is a special coated gloss finished paper, qualified for use in roll form for on-demand printing on the VP750 Inkjet printer.

BRADY B-7661 is used indoors and provides excellent photo quality results for product labelling and industrial applications.

REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.bradycanada.ca/products/labelsuse/rohs

All other regions: www.bradycanada.ca/weee-rohs

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Substrate -Adhesive -Total	0.104 mm 0.018 mm 0.122 mm
Adhesion to: -Stainless Steel -Glass -Polypropylene -Powder Coated Aluminium	ASTM D 1000 20 minute dwell	Destroys upon removal from all listed surfaces

PERFORMANCE PROPERTIES	TEST METHODS	TYPICAL RESULTS
High service temperature	30 days at 80°C (176°F)	Slight color changing of paper and inks
Low service temperature	30 days at -40°C (-40°F)	No visible effect
Humidity	30 days humidity chamber at 37°C (100°F) and 95% R.H.	No visible effect
UV Light Resistance	30 days in Xenon Test Chamber	Complete fading of the print
Abrasion resistance	Taber Abraser, CS-10 grinding wheels 250g/arm,200 cycles	Slight fading, print still legible

Shelf Life:

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80°F (27°C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.)

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2022 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady Europe | Poldergotestraat 9 | 9240 Zele | Belgium | Tel: +32 52.45.7811 | Fax: +32 52.45.7812