

BRADY B-821 SINGLE USE ACCIDENT PREVENTION TAGS

TDS No. B-821
 Effective Date: 11/13/2017

Description:

Brady B-821 Single Use Accident Prevention Tags with metal grommets.

Details:

Use:

Brady B-821 is designed for use as Accident Prevention Tags and custom tags for indoor use only.

Substrate Type:

Tyvek®

Standard Material Colors:

White

Standard Legend Colors:

Black and Red

Thickness (ASTM D 1593):

0.006 inch (0.1524 mm)

Abrasion Resistance (Method 5306 of U.S. Federal Test Method Std. No. 191A):

CS-10 wheels, 1000 g wts.
 Legend withstands up to 350 cycles

Service Temperature:

-40°F to 212°F (-40°C to 100°C)

Average Outdoor Durability:

Not recommended for outdoor use.

Chemical Resistance:

REAGENT	7 DAY IMMERSION	DIP TEST	RUB TEST
30% Sulfuric Acid	NE	NE	NE
10% Sulfuric Acid	NE	NE	NE
30% Hydrochloric Acid	NE	NE	NE
10% Hydrochloric Acid	NE	NE	NE
Glacial Acetic Acid	NE	NE	NE
5% Acetic Acid	NE	NE	NE
50% Sodium Hydroxide	NE	NE	NE
10% Sodium Hydroxide	NE	NE	NE
10% Ammonia	NE	NE	NE
5% Sodium Hypochlorite	NE	NE	NE
Methyl Ethyl Ketone	NE	NE	NE
10% Sodium Chloride	NE	NE	NE
Acetone	NE	NE	NE
Toluene	NE	NE	NE
Methanol	NE	NE	NE
Isopropyl Alcohol	NE	NE	NE
Heptane	NE	NE	NE
Mineral Spirits	NE	NE	NE
Turpentine	NE	NE	NE

Kerosene	NE	NE	NE
Diesel Fuel	NE	NE	NE
Gasoline	NE	NE	NE
ASTM #3 Oil	NE	NE	NE
SAE 20 Oil	NE	NE	NE
10% Sodium Chloride	NE	NE	NE
Alconox®	NE	NE	NE
Water	NE	NE	NE
Formula 409®	NE	NE	NE

NE = No Effect

F = Failed (affected Sample)

7 Day Immersion: Immersed in reagent for 7 days.

Dip Test: Five 10 minute dips in reagent with 30 minute recovery.

Rub Test: Rubbed sample for 1 minute with swab soaked in reagent.

Shelf Life:

Unlimited when stored at 70°F (21°C) and 40% to 50% R.H.

Trademarks:

Alconox® is a registered trademark of Alconox Co.

Company ASTM: American Society for Testing and Materials (U.S.A.)

Fed. Spec.: United States Federal Specification (U.S.A.)

Formula 409® is a registered trademark of the Clorox Company

SAE: Society of Automotive Engineers (U.S.A.)

Tyvek® is a registered trademark of Du Pont de Nemours, E.I. and

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2018 Brady Worldwide, Inc. | All Rights Reserved
 Material may not be reproduced or distributed in any form without written permission.