

BRADY B-8470 WHITE THERMAL TRANSFER PRINTABLE POLYPROPYLENE

TDS No. B-8470
Effective Date: 11/29/2020

Description:

GENERAL

Print Technology: Thermal transfer

Material Type: Polypropylene

Finish: Gloss

Adhesive: Permanent Rubber based adhesive

APPLICATIONS

B-8470 is designed to adhere to low surface energy materials.

REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.brady.co.jp/products/labelsuse/rohs

All other regions: www.bradyid.com/weee-rohs

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 100 Substrate Adhesive Total thickness (excluding liner)	0.0026 inch (0.0660mm) 0.0020 inch (0.0508mm) 0.0046 inch (0.1168mm)
Tack	ASTM D2979 Polyken™ Probe Tack 0.5 second dwell, 1cm/sec separation	2000 g
Adhesion	ASTM D 1000	
-Stainless Steel	20 minute dwell, RT 72 hr dwell, RT	130 oz/in (35 N/25mm) 135 oz/in (37 N/25mm)
-Polypropylene	20 minute dwell, RT 72 hr dwell, RT	103 oz/in (28 N/25mm) 117 oz/in (32 N/25mm)
Drop Shear	PSTC-7 (1/2" x 1" sample)	29 hours

Shelf Life:

Shelf life is eighteen months from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.) PSTC:

Pressure Sensitive Tape Council (U.S.A.)

Polyken™ is a trademark of Testing Machines Inc.

S. I.: International System of Units

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party,

independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2020 Brady Corporation Asia Pte. Ltd. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady Asia | 1 Kaki Bukit Crescent | Singapore 416236 | Singapore | Tel: 65 6477.7261 | Fax: 65 6748.7248