

## BRADY B-8472 WHITE THERMAL TRANSFER PRINTABLE POLYPROPYLENE

TDS No. B-8472  
Effective Date: 05/25/2023

### Description:

#### GENERAL

**Print Technology:** Thermal transfer

**Material Type:** Polypropylene

**Finish:** Glossy

**Adhesive:** Permanent Rubber based adhesive

#### APPLICATIONS

B-8472 is designed to adhere to low surface energy materials.

#### REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: [www.bradycanada.ca/weee-rohs](http://www.bradycanada.ca/weee-rohs)

In Europe: [www.bradyeurope.com/rohs](http://www.bradyeurope.com/rohs)

In Japan: [www.brady.co.jp/products/labelsuse/rohs](http://www.brady.co.jp/products/labelsuse/rohs)

All other regions: [www.bradyid.com/weee-rohs](http://www.bradyid.com/weee-rohs)

#### SPECIAL FEATURES

Brady B-8472 is compliant to the halogen requirements of IEC 61249-2-21 (2003-11)

### Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 100 -Substrate - Adhesive - Total thickness (excluding liner)	0.0026 inch (0.0660mm) 0.0015 inch (0.0381mm) 0.0041 inch (0.1041mm)
Tack	ASTM D2979 Polyken™ Probe Tack 0.5 second dwell, 1cm/sec separation	69.7 oz (1975 g)
Adhesion	ASTM D 1000	
-Stainless Steel	20 minute dwell, RT 72 hr dwell, RT	159 oz/in (44.2 N/25mm) 159 oz/in (44.2N/25mm)
-Polypropylene	20 minute dwell, RT 72 hr dwell, RT	135 oz/in (37.5 N/25mm) 135 oz/in (37.5 N/25mm)
Drop Shear	PSTC-7 (1/2" x 1" sample)	24 hours

### Shelf Life:

Shelf life is eighteen months from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

### Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.) PSTC:  
Pressure Sensitive Tape Council (U.S.A.)

Polyken™ is a trademark of Testing Machines Inc.

S. I.: International System of Units

**Note:** All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

#### **WARRANTY**

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2023 Brady Corporation Asia Pte. Ltd. | All Rights Reserved  
Material may not be reproduced or distributed in any form without written permission.

---

Brady Asia | 1 Kaki Bukit Crescent | Singapore 416236 | Singapore | Tel: 65 6477.7261 | Fax: 65 6748.7248