

BRADY BA-147 1 MIL ACRYLIC BASED ADHESIVE, SELF-WOUND ON A POLYESTER LINER

TDS No. BA-147
Effective Date: 03/05/2019

Description:

GENERAL

Material Type: Self-Wound, unsupported adhesive

Adhesive: Permanent acrylic

APPLICATIONS

BA-147 adhesive provides good bonding to a wide variety of substrates along with good temperature performance and good chemical resistance. Good high shear and high temperature performance. Aerospace, industrial, automotive and electronics markets.

REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.brady.co.jp/products/labelsuse/rohs

All other regions: www.bradyid.com/weee-rohs

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Liner -Adhesive	0.003 inch (0.0782 mm) 0.001 inch (0.0254 mm)
To perform the following tests, the exposed adhesive is laminated to a 2 mil polyester film. Adhesion samples are dwelled on panel, for the indicated time period.		
Adhesion to:	ASTM D 1000	
-Stainless Steel	20 minute dwell 72 hour dwell	48 oz/in (13 N/25 mm) 65 oz/in (18 N/25 mm)
-Polypropylene	20 minute dwell 72 hour dwell	28 oz/in (7.6 N/25 mm) 30 oz/in (8.1 N/25 mm)
-Polycarbonate	20 minute dwell 72 hour dwell	52 oz/in (14 N/25 mm) 73 oz/in (20 N/25 mm)
Tack	ASTM D 2979 Polyken™ Probe Tack 1 second dwell	60oz (500g)

Shelf Life:

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.)

Polyken™ is a trademark of testing Machines Inc.

S.I.: International System of Units

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2019 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289