

Brady Tsoft-160 Thermally Conductive Material Gap Filler

TDS No. BT-8607
Effective Date: 07/04/2010

Description:

GENERAL

Colour: Ice blue with gray backing

Binder: Silicone

Filler: Aluminium Oxide

Liner: Clear PE

Reinforcement: Fiberglass polyester

TSOFT-160 is a soft material designed to conduct heat away from uneven surfaces. The conformability allows for intimate contact over rough surfaces and eliminates air. Tsoft® materials are available in various thicknesses.

APPLICATION

Tsoft® materials are thermally conductive insulators typically mounted between a transistor and a heat sink offering low thermal resistance as well as electrical insulation. Tsoft® materials do not require thermal grease. Using Tsoft® materials can lead to dramatic production cost reductions and improved product uniformity eliminating messy grease mica application, contamination, mica cracking, silicone migration and drying out.

REGULATORY/AGENCY APPROVALS

RoHS: BT-8607 (Tsoft-160) is RoHS compliant in accordance to the EU Directive 2002/95/EC and its amendments.

Details:

PHYSICAL PROPERTIES	TEST METHOD	TYPICAL RESULTS
Thickness	ASTM D374	160 mil (4mm)
Specific Gravity	ASTM D792	2.3 g/cm ³
Hardness (Shore A)	ASTM D2240	15
Elongation, minimum	ASTM D828	3%
ELECTRICAL PROPERTIES		
Dielectric Strength	ASTM D149 (Type 1)	12 KV
Volume Resistivity	ASTM D257	2.5 E+13 Ohm.cm
Dielectric Constant, 60Hz	ASTM D150	5.5
Dissipation Factor, 60Hz	ASTM D150	0.0039
THERMAL PROPERTIES		
Thermal Conductivity @ 10psi	ASTM E1530 (modified ASTM D5470)	1.0 W/mK
Thermal Impedance @ 10psi	ASTM D5470	6.0 C-in ² /Wattt
Continuous Use Temperature	MIL-I-49546A	-60°C to 200°C
Weight Loss, 24 hrs @ 200 C	-	< 1%

Available Forms:

Tsoft® thermal management materials are available in roll form, sheet form, standard and special configurations.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.)

UL: Underwriters Laboratories Inc. (U.S.A.)

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to

manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2016 Brady Corporation Asia Pte. Ltd. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.

Brady Asia | 1 Kaki Bukit Crescent | Singapore 416236 | Singapore | Tel: 65 6477.7261 | Fax: 65 6748.7248